

IN THE CLAIMS

31 Claims 1-4 (Cancelled)

Claims 5-12 (Withdrawn)

Claim 13 (Cancelled)

RECEIVED  
JUN 10 2003  
TC 1700

14. (Newly Added) An anisotropic exchange spring magnet powder made by a process comprising the steps of:

preparing a crystalline mother material containing a hard magnetic material phase containing a rare earth metal element, a transition metal element, and at least one element selection from the group consisting of boron (B), carbon (C), nitrogen (N) and oxygen (O), and a soft magnetic material phase containing a transition metal element, and at least one element selected from the group consisting of boron (B), carbon (C), nitrogen (N) and oxygen (O), wherein the content of said rare earth metal element is from 2 to 15 atomic %, and the content of at least one element selected from the group consisting of boron (B), carbon (C), nitrogen (N) and oxygen (O) is from 1 to 25 atomic %, and wherein the crystalline mother material having a content of amorphous parts of magnetization of 95% or less;

amorphising said crystalline mother material,

crystallizing said crystalline mother material amorphised in said amorphising process,

repeating a continuous process composed of said amorphising process and crystallizing process, one or more times.

15. (Newly Added) An anisotropic exchange spring magnet powder according to the process of claim 14, said crystallizing process further comprising the steps of placing said crystalline mother material in magnetic field, and compressing said crystalline mother material placed in magnetic field in said placing process.

16. (Newly Added) An anisotropic exchange spring magnet powder according to the process of claim 14, wherein said amorphising process is conducted under a condition in which oxygen is blocked, in any of vacuum, an inert gas, nitrogen and an organic solvent.

17. (Newly Added) An anisotropic exchange spring magnet powder according to the process of claim 14, wherein said crystallizing process is conducted under a condition in which oxygen is blocked, in any of vacuum, an inert gas, nitrogen and an organic solvent.

18. (Newly Added) An anisotropic exchange spring magnet powder according to the process of claim 14, wherein said crystallizing process has a crystallization heating treatment temperature of 950°C or less.

Q1

19. (Newly Added) An anisotropic exchange spring magnet powder according to the process of claim 14, wherein said crystallizing process has a crystallization heating treatment time of 1 hour or less.

671

\_\_\_\_\_